



HEAT ACTIVATED

TRANSFER ADHESIVES

RD-594

0.100mm
0.230mm

- Original heat activated – heat curing – zero tack nitrile rubber/resin

RD-461

0.025mm

- Thin layer of adhesive suitable for lightweight substrate splicing

RD-573

0.100mm
0.200mm

- Tackier version of RD-594
- Build up adhesion bond strength more quickly and at lower temperatures

RD-614

0.100mm

- Version of RD-594 without filler
- Suitable for splicing of thicker substrates

RD-685

0.100mm
0.200mm

- Equivalent to Technical 8401 & 8410 – recommended for the splicing of non-woven glass substrates used in the manufacture of PVC flooring



RD-594

nitrile rubber/phenolic resin transfer adhesive tape

a heat curing adhesive based on nitrile rubber/phenolic resin

This adhesive has a high rubber content and therefore has a high initial shear strength, particularly at high temperatures. Curing of the adhesive will also improve this shear strength.

Application:

- *Laminating adhesive for high strength permanent bonding of metals, plastics and cloths.*
- *Excellent adhesion to PVC. The cured adhesive is heat and solvent resistant.*

RD-573

RD-614

RD-685

nitrile rubber/phenolic resin transfer adhesive tape

a heat curing adhesive based on nitrile rubber/phenolic resin

Application:

- *Laminating adhesive for high strength permanent bonding of metals, plastics and cloths.*
- *Excellent adhesion to PVC. The cured adhesive is heat and solvent resistant.*

RD-461

nitrile rubber/phenolic resin transfer adhesive tape

a heat curing adhesive based on nitrile rubber/phenolic resin, coated onto a siliconised paper interliner

Application:

- *Laminating adhesive for high strength permanent bonding of metals, plastics and cloths.*
- *Excellent adhesion to PVC. The cured adhesive is heat and solvent resistant.*