

PETROLEUM TOTAL COKE
FOR GRAPHITE PRODUCTION
www.exportimportworldtm.com

№	Description of Index	Figure
1	Mass portion of the total moisture,%,not more than	3,0
2	Ash content,%, not more than	0,6
3	Mass portion of sulfur,in%, not more than	0,6
4	Mass portion of flying substances,%,not more than	11,0
5	Real density after warming up at 1300°C in a current of 5 hours,g/sm ³ , not less than	2,08
6	Mass portion of coke with the size of pieces not less than 8 mm,%, not more than	60

Note: The position №1 is not rejection and defined for calculation with consumer

С Н Е Н С М М А Р Н Д
Р А И И Р А Н Н П Р Д И И

www.exportimportworldtm.com

№	Наименование показателей	Норма
1	Массовая доля общей влаги, %, не более	3,0
2	Зольность, %, не более	0,6
3	Массовая доля серы, %, не более	0,6
4	Массовая доля летучих веществ, %, не более	11,0
5	Действительная плотность после прокаливания при 1300 °С в течении 5-ти часов, г/см ³ не менее	2,08
6	Массовая доля кокса с размером кусков менее 8 мм, %, не более	60

ПРИМЕЧАНИЕ: массовая доля общей влаги не является браковочным показателем и служит для расчета с потребителем.